

Application No.: 10/089,261
Filing Date: March 26, 2002
Page: 2

Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) ~~Use of a multilayered polypropylene film as~~ An in-mold label in the a blow-molding process ~~[[,]] in which the label film is laid in the mold of a blow molding machine and has comprising a multilayered polypropylene film. said film comprising a base layer disposed between~~ an inner top layer facing the a container to be molded and an outer top layer in contact with the a mold, ~~characterized in that the~~ said inner top layer has exhibiting a roughness Rz of at least 3.5 μm .

2. (Currently Amended) ~~Use~~ An in-mold label according to claim 1, ~~characterized in that~~ wherein the inner top layer comprises a mixture of at least two polymers which are not compatible with one another.

3. (Currently Amended) ~~Use~~ An in-mold label according to claim 2, ~~characterized in that~~ wherein the mixture consists of a polyethylene and polypropylene or polypropylene copolymer~~[[,]] preferably propylene copolymer.~~

4. (Currently Amended) ~~Use~~ An in-mold label according to claim 2 ~~and/or 3,~~ characterized in that wherein the mixture comprises PE and PP in a ratio of from 5 to 50% by weight ~~(weight ratio) of PE:PP~~ ~~[[=]] 1:12 to 5:1.~~

5. (Currently Amended) ~~Use~~ An in-mold label according to claim 1, ~~characterized in that the~~ wherein the base layer is an opaque layer and that comprises vacuole-initiating fillers, and the density of the film is from 0.65 to 0.85 g/cm^3 .

Application No.: 10/089,261

Filing Date: March 26, 2002

Page: 3

6. (Currently Amended) ~~Use~~ An in-mold label according to ~~one or more of claim~~[[s]] 1 to 5, ~~characterized in that wherein~~ the thickness of the film is at least 50 μm ~~[[,]] preferably from 75 to 120 μm .~~

7. (Currently Amended) ~~Use~~ An in-mold label according to ~~one or more of claim~~[[s]] 1 to 6, ~~characterized in that wherein~~ the thickness of the inner top layer is between 0.5 and 5 μm .

8. (Currently Amended) ~~Use~~ An in-mold label according to ~~one or more of claim~~[[s]] 1 to 7, ~~characterized in that wherein~~ the thickness of the outer top layer is between 0.3 and 5 μm .

9. (Currently Amended) ~~Use~~ An in-mold label according to ~~one or more of claim~~[[s]] 1 to 8, ~~characterized in that wherein~~ the film comprises ethoxylated fatty acid amide in its base layer.

10. (New) An in-mold label according to Claim 2, wherein the mixture comprises polyethylene and polypropylene in a weight ratio of polyethylene to polypropylene of from 1:12 to 5:1.

11. (New) An in-mold label according to claim 1, wherein the roughness is induced by increasing the formation of β -spherulites within said inner top layer.

12. (New) A method of using a multilayered polypropylene film as an in-mold label in a blow-molding process in which the label film is laid in the mold of a blow-molding machine and has an inner top layer facing a container to be molded and an outer top layer in contact with a mold, said inner top layer exhibiting a roughness R_z of at least 3.5 μm .

13. (New) A method according to claim 12, wherein the inner top layer comprises a mixture of at least two polymers which are not compatible with one another.

Application No.: 10/089,261

Filing Date: March 26, 2002

Page: 4

14. (New) A method according to claim 13, wherein the mixture consists of a polyethylene and polypropylene or polypropylene copolymer.

15. (New) A method according to claim 13, wherein the mixture comprises PE and PP in a ratio of from 5 to 50% by weight.

16. (New) A method according to claim 12, wherein the base layer is an opaque layer that comprises vacuole-initiating fillers, and the density of the film is from 0.65 to 0.85 g/cm³.

17. (New) A method according to claim 12, wherein the thickness of the film is at least 50 μ m.

18. (New) A method according to claim 12, wherein the thickness of the inner top layer is between 0.5 and 5 μ m.

19. (New) A method according to claim 12, wherein the thickness of the outer top layer is between 0.3 and 5 μ m.

20. (New) A method according to claim 12, wherein the film comprises ethoxylated fatty acid amide in its base layer.

21. (New) A method to Claim 13, wherein the mixture comprises polyethylene and polypropylene in a weight ratio of polyethylene to polypropylene of from 1:12 to 5:1.